

Kane Ara Sepahan

Producer of minerals & Supplier of Chemicals

Natrual Asphalt (Gilsonite 10 - 15)

Description	Quality
Color in Mass	Black
Color in Streak or Powder	Brown
Softening Point	200-240 C
Moisture Content	<3
Specific Gravity @ 77° F	1.04 – 1.06
Hardness (Mohr 's Scale)	2
Penetration	0
Flash Point, ° C, C.O.C	280<
Trace Elements	<1
Volatile Matter	55-70
Ash	10-15
Fixed Carbon	20-30

