

Kane Ara Sepahan

Producer of minerals & Supplier of Chemicals

SPECIFICATION OF Gilsonite

Analysis	SPECIFICATION	Test method
Ash	MAX 5±1 %	ASTM – D 3174
Mesh Size	200	
density	1.05	ASTM – D 70
Moisture	Max 2%	ASTM – D 3173
Softening Point C	MAX 230±5	ASTM – D 36

<https://kaneara.com>

info@kaneara.com

No. 5-25, In front of Third side street, Fifth Street, Phase 1, Sajzi Industrial Zone, Isfahan, Iran